

CONTRAFLAM STRUCTURE 30 Elegance

Fire resistant laminated safety glass for interior application

CLASSIFICATION



EI = Insulation

Ability to withstand fire exposure without transmission of fire to the non-fire side as a result of the passage of flames, hot gases or significant conduction of heat, thereby causing ignition of the non-fire exposed surface or materials in contact, and provides a barrier to heat to protect people.

AVAILABLE OPTIONS



+ Protection



+ Coloring
+ Digital printing
+ Matt finished
+ Screen printing
+ Shapes



+ Extra clear
+ Noise control

Contact us to personalize your solution to meet your project requirements.

TECHNICAL SPECIFICATIONS

Fire resistance	EI 30 (EN 13501-2)
Reaction to fire	A2-s1, d0 (EN 13501-1)
Impact resistance	1(B)1 (EN 12600)
UV stability / Durability	Extended exposure time of 5000 hrs UV versus normative 2000 hrs* (*EN ISO 12543-4)
Application conditions	Restricted to interior applications. See Vetrotech Quality and Application Guidelines
Certificate of constancy of performance	0336-CPR-5064C-IL - AVCP System 1
Hazardous material contained	None
Assembly	According to the Vetrotech Installation Guideline
Dimensional tolerances (width/height)	≤1000 mm: -1/+2 mm ≤2000 mm: -1/+2.5 mm >2000 mm: -1/+3 mm

Product / CE / DoP-Code	Y7223950	Y7223951
Nominal thickness	23 mm	28 mm
Maximum glass size	1500 x 3000 mm	2160 x 3210 mm
Thickness tolerance	+2 / -2 mm	+2 / -2 mm
Weight	51.5 kg/m ²	64.0 kg/m ²
Sound reduction Rw (EN 140-3)	42 (-3, -3) dB	43 (-2, -3) dB
Light transmission (EN 410)	85%	83%
Light reflection pL ext./int. (EN 410)	9% / 9%	9% / 9%
U value, W/m ² K (EN 673)	4.6	4.5
g value (EN 410)	0.7	0.68
Energy transmission tE (EN 410)	64%	61%

Products with PVB laminated interlayers are available, if required by projects or national regulation.
Shapes: dimensional tolerances may vary +1 mm.
DoP: Declaration of Performance - available upon request from your sales office.