

CONTRAFLAM 30 Horizontal

Fire resistant laminated safety glass for interior application

CLASSIFICATION



EI = Insulation

Ability to withstand fire exposure without transmission of fire to the non-fire side as a result of the passage of flames, hot gases or significant conduction of heat, thereby causing ignition of the non-fire exposed surface or materials in contact, and provides a barrier to heat to protect people.

AVAILABLE OPTIONS



- + Alarm
- + EMS shielding
- + Floors
- + Protection



- + Coloring
- + Digital printing
- + Matt finished
- + Screen printing
- + Shapes



- + Climate control
- + Dynamic privacy
- + Extra clear
- + Noise control



- + Double glazing
- + Self-cleaning
- + Solar control
- + Tinting
- + Triple glazing

Contact us to personalize your solution to meet your project requirements.

TECHNICAL SPECIFICATIONS

Fire resistance

EI 30 (EN 13501-2)

Reaction to fire	B-s1, d2 (EN 13501-1)
Impact resistance	1(B)1 (EN 12600)
UV stability / Durability	Extended exposure time of 5000 hrs UV versus normative 2000 hrs* (*EN ISO 12543-4)
Application conditions	Avoid prolonged exposure to elevated temperatures. See Vetrotech Quality and Application Guidelines
Certificate of constancy of performance	0336-CPR-5064C/IL - AVCP System 1
Hazardous material contained	None
Dimensional tolerances (width/height)	≤1000 mm: -1/+2 mm ≤2000 mm: -1/+2.5 mm >2000 mm: -1/+3 mm

Product / CE / DoP-Code

Y7223023

Nominal thickness	21 mm
Maximum glass size	1250 x 3000 mm
Thickness tolerance	+2 / -1 mm
Weight	44.8 kg/m ²
Sound reduction Rw (EN 140-3)	40 (-1, -2) dB
Light transmission (EN 410)	86%
Light reflection pL ext./int. (EN 410)	9% / 9%
U value 0°/30°/60°/90°, W/m ² K (EN 673)	5.4/5.4/4.8/4.6
g value (EN 410)	0.69
Energy transmission tE (EN 410)	62%
Variant	STADIP 44.2

Shapes: dimensional tolerances may vary +1 mm.

DoP: Declaration of Performance - available upon request from your sales office.